

Copper Powder PMS-K (GOST 4960-75)

Технические характеристики

Nominal size of powder particles: 0,45 mm
According to Svelen Co. Ltd. technical conditions, it is possible to manufacture copper powder with nominal size of particles: up to 0,8 mm or up to 1 mm.

Consistency:

Weight percent of copper - not less than 99,5%;
Impurity content according to GOST 4960-75

Срок изготовления

30 days

Упаковка

Metallic Drums

Copper powder is packed in metallic drums, drums with polyethylene liner bag according to GOST 5044 and GOST 17811, or soft polymeric package of big-bag type.

Storage

Guaranteed shelf life - not less than 6 months after the manufacture date. Powder must be stored in indoor storages at the temperature not more than +350C. Powder must be protected from pollutions, atmospheric fallouts and other aggressive mediums.

